



Linear Low-Density Polyethylene Compound

For Blown film, Stretch Film, Home appliance, Industry and other utility products.

Color: Natural

Processing method: Blown film, Casting Film

Specification:

Code:SH

Typical value	Value	Unit	Test method
Melt flow index (190° C/2.16kg)	0.9±0.2	g/10min	ASTM D1238
Density	0.92±0.02	g/cm ³	ISO 1183
Moisture	Max 0.2	%	ASTM D644
Tensile Strength @ Break (MD/TD)	37/27	MPa	ISO 527
Elongation @ Break (MD/TD)	>400/750	%	ISO 527

