



# TECHNICAL DATA SHEET

## Oxidized Polyethylene Wax — Grades 2401, 2452 and 2453

### Product Description

Oxidized polyethylene waxes contain polar functional groups. Grades 2401 and 2452 act as lubricants and release agents in PVC processing. Grade 2453 supports emulsification for use in water-based systems.

### Physical Characteristics

| Property                    | Test Method | Grade 2401                    | Grade 2452                    | Grade 2453                    |
|-----------------------------|-------------|-------------------------------|-------------------------------|-------------------------------|
| Viscosity at 140°C          | ASTM D3236  | 20 ± 10 cP                    | 50 ± 20 cP                    | 40 ± 20 cP                    |
| Ring & Ball Softening Point | ASTM E28    | 105 ± 10°C                    | 105 ± 5°C                     | 105 ± 5°C                     |
| Density at 25°C             | ASTM D611*  | 0.92 ± 0.01 g/cm <sup>3</sup> | 0.92 ± 0.01 g/cm <sup>3</sup> | 0.93 ± 0.01 g/cm <sup>3</sup> |
| Acid Number                 | ASTM D1386  | 20 ± 3 mg KOH/g               | 17–20 mg KOH/g                | 25–30 mg KOH/g                |
| Color                       | —           | Milky white                   | Yellowish                     | Yellowish                     |
| Form                        | —           | Flake                         | Pastille                      | Flake                         |

\*Density test method reproduced from the original data sheets; confirmation with the supplier is recommended.

### Applications

| Grade | Applications                                                                    |
|-------|---------------------------------------------------------------------------------|
| 2401  | Lubricant and release agent in PVC processing                                   |
| 2452  | Lubricant and release agent in PVC processing                                   |
| 2453  | Textile auxiliaries, waterborne lacquers, printing inks, and leather processing |

### Storage and Shelf Life

Store in dry conditions at room temperature. Minimum shelf life is one year from the date of manufacture when properly stored.

### Technical Note

Customers should check product quality and suitability before commercial use. The original data sheets state that no guarantee or warranty applies after processing.